

Operating Procedure
Title: Inspection of Scrap

ATTACHMENT 1 - GENERAL SCRAP SPECIFICATIONS

Definitions:

“Downgrade” – When a particular grade of scrap is found to not conform to its represented grade, it may be, by agreement by SDI-RBD and supplier, accepted as an inferior grade of scrap.

“Free of” – When specified to be “Free of”, the grade shall not contain any amount of prohibited material in any amount greater than that which is deemed harmful to the steelmaking process.

“Grade” – A classification of scrap type based upon Institute of Scrap Recycling Industries (ISRI) ferrous scrap classification or SDI-RBD/vendor description.

The following specifications apply to all the scrap purchased by Steel Dynamics® Roanoke Bar Division (SD-RBD). All material is to be suitable and acceptable to SD-RBD based on inspection.

1. All grades of scrap shall not contain significant amounts of high-carbon or high-alloy steel (e.g. alloy steel, chrome plated steel, stainless steel, cast iron material, high manganese scrap, high silicon scrap); nonferrous metals (e.g. aluminum, copper, brass, lead,); non-metallics (e.g. dirt, wood, concrete, insulation, rubber, plastic, cloth, paper, oil, grease, or any other non metallic materials); or any other scrap deemed detrimental to our steel making processes.
2. Material containing lead will not be accepted (e.g. batteries, lead-based paints, gas tanks, metal guttering, otherterne plated material, mufflers, tail pipes, motor blocks, wheel weights, babbitt, radiators, lead joints).
3. Loads having potentially explosive material (e.g. tanks, cylinders, aerosol cans, shocks, transmissions, torque converters, air conditioning units, gear boxes, metal guttering radiators, electric motors, any item likely to hold oil) will not be accepted.
4. Sealed units cannot be accepted. If a load contains sealed units, two 5 in. holes must be cut on each end before the load can be accepted. Sealed units should be situated in the load such that they are visible for inspection at SD-RBD. Cylinders can be accepted if they are cut in half through the barrel.
5. In the specifications, unless noted otherwise, the following maximum chemistry limits will apply.

Operating Procedure

Title: Inspection of Scrap

0.45% max Cu (copper)	0.06% max Mo (molybdenum)
0.20% max Cr (chromium)	0.50% max Si (silicon)
1.65% max Mn (manganese)	0.05% max P (phosphorous)
0.25% max Ni (nickel)	0.05% max S (sulfur)
0.03% max Sn (tin)	

6. Material bought as "special low residual" scrap must not exceed the following maximum chemistry limits.

0.10% max Cu	0.02% max Mo	0.08% max Cr
0.25% max Si	0.90% max Mn	0.015% max P
0.08% max Ni	0.01% max S	0.01% max Sn

7. A car must not be top-dressed with material that does not constitute a major portion of the material in the car and precludes visual inspection of the car.
8. #1 and #2 Bundles must be free of dirt and non-metallics at the center of the bundle.
9. SD-RBD must approve any exceptions to these specifications. On normal grades, SD-RBD may, at times, test other materials that may exceed the above chemistry on controlled usage. (Material will be rejected if delivered in a frameless trailer.)
10. All grades shall be free of hazardous materials, including, but limited to, asbestos, electronic waste (to the extent practicable), explosives, flammable material, hazardous waste, military scrap, oil-filled devices, radioactive material, or refrigerants.
11. All scrap must be depleted to the extent practicable of chlorinated plastics. Materials that may contain chlorinated plastics include, but are not limited to, consumer products, containers, or plastic motor vehicle components.
12. All scrap must be depleted to the extent practicable of mercury and mercury-containing materials. Materials that may contain mercury include but are not limited to mercury-wetted or -containing relays, switch gears, rectifiers, gauges, manometer, barometers, thermometers, and fluorescent lighting fixtures.
13. Any scrap received not meeting our scrap specification requirements will be subject to a downgrade or full rejection based on the severity of nonconforming material. If unloaded in a production area, immediate downgrade or rejection can occur with photographic documentation.
14. Supplier will be responsible for the cost of freight to return rejected scrap and for a downgrade that is not accepted by the supplier.

Operating Procedure

Title: Inspection of Scrap

SDI-RBD SCRAP SPECIFICATION REQUIREMENTS

Grade: #2 Shred				Industry ID: ISRI #s 210, 211, 212						
Description: Iron and steel scrap, magnetically separated										
Typical Appearance: 					Typical Constituents: - Automobiles - Unprepared #1 heavy melt - Unprepared #2 heavy melt - Miscellaneous bailing and sheet scrap					
Sizing	Thickness (max)			4"		Typical Density			65 – 90 (lbs / ft³)	
	Length and Width (max)			4" x 10"						
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	
Maximum (wt%)	1.50	0.04	0.04	0.20	0.30	0.20	0.15	0.03	0.04	
Prohibitions: - Municipal scrap - Incinerator scrap - Lead coated - Vitreous enameled materials - Tin cans - Excessive fluff - Copper clad or plated steel - Excessive copper wiring and motor winding - Stampings - Punchings - Electrical material - Free of dirt										
Additional Notes: Cast iron content shall not exceed 2% by weight										

Operating Procedure

Title: Inspection of Scrap

Grade: Plate and Structural				Industry ID: ISRI #s 231, 232, 236					
Description: - Clean cut structural and plate scrap, heavy gauge - Clean cut structural shape crop ends, shearings, or broken steel wheels									
Typical Appearance: 					Typical Constituents: - Structural Items - Plates - Large diameter pipe - Heavy walled pipe				
Sizing	Thickness			$\frac{1}{4}" - 8"$		Typical Density			60 – 70 (lbs / ft ³)
	Length and Width (max)			4' x 2'					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	1.50	0.04	0.05	0.60	0.25	0.25	0.25	0.03	0.015
Prohibitions: - Die blocks - Cut up machinery - Cam shafts - Crank shafts - Torque converters - Cables - Chains - Springs - Gears or gear boxes - Transmissions - Electrical panels - Motors or motor blocks of any kind - Counterweights - Rebar - Cast iron - Free of dirt - Galvanized									
Additional Notes:									

Operating Procedure

Title: Inspection of Scrap

Grade: #2 Heavy Melt				Industry ID: ISRI #s 203, 204, 205						
Description: - Steel scrap, black or galvanized 1/8" thickness and over - May include automotive scrap if properly prepared (rear end, torque converters, and transmissions must be cut and drained) - Free of sheet iron and thin gage material										
Typical Appearance: 					Typical Constituents: - Small diameter pipe - Automotive wheel rims - Reinforcing bar - Prepared automotive parts - Post-consumer steel goods - Light-weight structural items - Small machinery parts					
Sizing		Thickness			1/8" - 8"		Typical Density			40 – 55 (lbs / ft ³)
		Length and Width (max)			4' x 2'					
Chemistry		Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)			0.04	0.07		0.6	0.25	0.25	0.05	0.05
Prohibitions: - Municipal scrap - Turnings - Cables - Chains - Wire - Powder metallurgy parts and non-metallics - Electrical steels - Stainless steels - Tin coated steels - Lead coated steel - Vitreous enameled materials - White goods - Electric motors - Free of dirt										
Additional Notes: - Heavy walled pipe is acceptable up to 10% of load; over 4" must be split - Rear ends, torque converters, and transmissions must have a 5" hole cut on both ends and drained - Can contain up to 25% galvanized - Cast iron is not to exceed 2% by weight. - Cylinders must be cut in half through the barrel										

Operating Procedure

Title: Inspection of Scrap

Grade: #1 Heavy Melt				Industry ID: ISRI #s 200, 201, 202					
Description: Clean steel scrap at least ¼" thickness									
Typical Appearance: 					Typical Constituents: - Structural Items - Plates - Truck Parts - Large machinery parts				
Sizing	Thickness			¼" - 8"		Typical Density			45 – 60 (lbs / ft³)
	Length and Width (max)			4' x 2'					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)		0.05	0.05	0.50	0.35	0.25	0.25	0.06	0.03
Prohibitions: - No automotive scrap - Gears - Cables - Chains - Powder metallurgy parts and non-metallics - Electrical steels - Stainless steels - Tin coated steels - Lead coated steel - Vitreous enameled materials - White goods - Free of dirt - Cast iron									
Additional Notes: - Heavy walled pipe is acceptable; over 4" must be split - Dies must be "by approval" only									

Operating Procedure

Title: Inspection of Scrap

Grade: Busheling				Industry ID: ISRI #s 207					
Description: Clean steel scrap, including new factory busheling									
Typical Appearance: 					Typical Constituents: - Sheet clippings - Stamping - Flashings				
Sizing	Thickness			20 Gauge -		Typical Density			60 – 75 (lbs / ft ³)
	Length and Width (max)			3' x 3'					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	0.80	0.03	0.05	0.40	0.10	0.10	0.10	0.03	0.02
Prohibitions: - Old auto body or fender stock - Tin or lead-coated materials - Limes, vitreous enameled materials - Free of dirt									
Additional Notes: Electrical steel over 0.50% Si is prohibited									

Operating Procedure

Title: Inspection of Scrap

Grade: #1 Bundles				Industry ID: ISRI #s 208					
Description: Clean steel scrap, busheling, clippings, sheet, or skeleton scrap compressed into a bundle									
Typical Appearance: 					Typical Constituents: Hydraulically compressed bundles consisting of: - Busheling - Clippings - Punches - Sheet steel				
Sizing	Thickness			2'		Typical Density			75 – 90 (lbs / ft³)
	Length and Width (max)			4' x 2'					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	1.50	0.05	0.05	0.50	0.10	0.10	0.10	0.03	0.01
Prohibitions: - Auto body or fender stock - Metal coated, like tin or lead-coated materials - Limes, vitreous enameled materials - De-tinned materials - Free of dirt - Free of cast iron									
Additional Notes: - Maximum for all dimensions is 48"(4'), but no two dimensions can be over 24"(2') - Example, 48" x 24" x 24" is acceptable, 48" x 36" x 24" and 60" x 24" x 24" are not - A maximum of 10% galvanized is allowable - Minimum density is 75 lbs / ft³									

Operating Procedure

Title: Inspection of Scrap

Grade: #2 Bundles				Industry ID: ISRI #s 209, 218					
Description: - Old black and galvanized sheet steel hydraulically compressed into rectangular cubes - Unprepared #2 heavy melt hydraulically compressed into rectangular cubes for the purpose of increasing density									
Typical Appearance: 					Typical Constituents: "post consumer" goods "white goods" (appliance shells) - Used sheet goods (siding, canning stock, etc) - Low density #2 heavy melt				
Sizing	Thickness			2'		Typical Density			60 – 70 (lbs / ft ³)
Length and Width (max)					4' x 2'				
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%) Maximum chemistries are difficult to determine due to large content variety from bundle to bundle									
Prohibitions: - Auto body or fender stock - Metal coated, like tin or lead-coated materials - Limes, vitreous enameled materials - De-tinned materials - Motor blocks - Transmissions - Electrical motors - Shock absorbers - Tin cans - Electrical materials - Non-metallics within bundles - Free of dirt - Free of cast iron									
Additional Notes: - Maximum for all dimensions is 48"(4'), but no two dimensions can be over 24"(2') - Example, 48" x 24" x 24" is acceptable, 48" x 36" x 24" and 60" x 24" x 24" are not - A maximum of 40% galvanized is allowable - Minimum density is 60 lbs / ft³									

Operating Procedure

Title: Inspection of Scrap

Grade: Turnings				Industry ID: ISRI #s 219, 220, 221, 222, 223					
Description: Machine shop and/or short shoveling turnings.									
Typical Appearance: 					Typical Constituents: Byproduct due to: - Lathing - Drilling - Boring - Machining - Etc.				
Sizing	Thickness			NA		Typical Density			60 – 70 (lbs / ft ³)
	Length and Width (max)			NA					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)		0.10	0.08	0.20	0.40	0.70	0.80	0.03	0.03
Prohibitions: 3 wt% oil 5 wt% rust 1 wt% water - Scale - Over-Oxidized - Springy material - Tangled material - Matted material - Free of cast iron - Free of dirt									
Additional Notes:									

Operating Procedure

Title: Inspection of Scrap

Grade: A Scrap				Industry ID:						
Description: Reprocessed slag and skulls										
Typical Appearance: 				Typical Constituents: - EAF Slag - LMF Slag - Tundish Skulls - EAF and LMF Skulls						
Sizing		Thickness		4" – 4'		Typical Density		40 – 60 (lbs / ft ³)		
Length and Width		4" x 4" - 4' x 4'								
Chemistry		Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)		Steel chemistry will be that of RBD product steel and slag chemistry will be that of RBD slag.								
Prohibitions: - Must be at least 65 wt% steel (less than 40 wt% slag and dirt) - Free of dirt										
Additional Notes:										

Operating Procedure

Title: Inspection of Scrap

Grade: B Scrap				Industry ID:						
Description: Reprocessed slag and skulls										
Typical Appearance: 					Typical Constituents: - EAF Slag - LMF Slag - Tundish Skulls - EAF and LMF Skulls					
Sizing		Thickness		$\frac{3}{4}" - 4"$		Typical Density			90 – 120 (lbs / ft ³)	
		Length and Width		$\frac{3}{4}" \times \frac{3}{4}" - 4" \times 4"$						
Chemistry		Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)		Steel chemistry will be that of RBD product steel and slag chemistry will be that of RBD slag.								
Prohibitions: - Must be at least 45 wt% steel (less than 60 wt% slag and dirt) - Free of dirt										
Additional Notes: Only up to contractual maximum will B scrap be accepted										

Operating Procedure

Title: Inspection of Scrap

For the following, a meltshop metallurgist should be contacted in order to resume the inspection:

Grade: Railroad rail and OTM				Industry ID: ISRI #s 4, 5, 6, 17, 18, 18A, 24, 27, 28A, 28B, 28C, 29					
Description: Cropped railroad rail and other track material									
Typical Appearance: 					Typical Constituents: - Railroad track - Railroad spikes - Fastening plates				
Sizing	Thickness			NA		Typical Density			55 – 65 (lbs / ft ³)
	Length and Width (max)			4' x 4'					
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	1.50	0.05	0.05	0.6	0.20	0.30	0.15	0.03	0.10
Prohibitions: - OTM must be 3' and under - Railroad timbers - Free of dirt									
Additional Notes: - Rail that is heavier than 80 lbs per yard will be cut to 4' and below - Rail that is lighter than 80 lbs per yard will be cut to 3' and below									

Operating Procedure

Title: Inspection of Scrap

Grade: Flashing				Industry ID:						
Description: Shredded steel flashing and siding										
Typical Appearance: 					Typical Constituents: - Flashing - Siding					
Sizing		Thickness (min)		1/8"		Typical Density			50 – 70 (lbs / ft ³)	
		Length and Width (max)		3' x 3'						
Chemistry		Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)			0.02	0.02	0.30	0.10				
Prohibitions: - Springy material - Gushy material - Tangled material - Matted material - Free of dirt										
Additional Notes: Suitable for magnetic handling										

Operating Procedure

Title: Inspection of Scrap

Grade: Galvanized #1 Busheling				Industry ID:					
Description: Clean steel scrap, including new factory busheling									
Typical Appearance: 					Typical Constituents: - sheet clippings - stamping - flashing				
Sizing		Thickness (min)		20 gauge		Typical Density			60 – 75 (lbs / ft ³)
Length and Width (max)		3' x 3'							
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	0.60	0.02	0.02	0.30	0.10	0.08	0.08	0.02	0.02
Prohibitions: - Old auto body or fender stock - Tin or lead-coated materials - Limes, vitreous enameled materials - Free of dirt									
Additional Notes:									

Operating Procedure

Title: Inspection of Scrap

Grade: #1 Railroad Steel					Industry ID: ISRI #s 2, 2A, 3, 3A, 45, 45A				
Description: Rail cars cut to length									
Typical Appearance: 					Typical Constituents: - Bolsters - Truck sides - Frames - Car sides				
Sizing	Thickness (min)				3/16"		Typical Density		55 – 65 (lbs / ft ³)
	Length and Width (max)				3' x 2'				
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)					0.5				
Prohibitions: - Car sides may only be a maximum of 20 wt% of total load 3% rust - Free of dirt									
Additional Notes:									

Operating Procedure

Title: Inspection of Scrap

Grade: Cast Iron				Industry ID: ISRI #s 12, 13, 14					
Description: Automotive and other cast iron									
Typical Appearance: 					Typical Constituents: - Automotive - Machinery - Wear components				
Sizing	Thickness				NA		Typical Density		60 – 70 (lbs / ft ³)
	Length and Width (max)				4' x 2'				
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)		0.03	0.07		0.4	0.15	0.20	0.04	0.03
Prohibitions: - Oil exceeding 2 wt% - Rust exceeding 2 wt% - Free of dirt - Scale - Nonferrous metals									
Additional Notes: Cast iron contains 2-3% Si and 2-4% C									

Operating Procedure

Title: Inspection of Scrap

Grade: Railroad Wheels					Industry ID: ISRI # 42				
Description: Railroad car wheels									
Typical Appearance: 					Typical Constituents: Railroad car wheels				
Sizing	Thickness				NA		Typical Density		75 – 95 (lbs / ft ³)
	Length and Width (max)				NA				
Chemistry	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn
Maximum (wt%)	1.50	0.04	0.04	0.30	0.25	0.30	0.20	0.03	0.02
Prohibitions: - Oil exceeding 1 wt% - Rust exceeding 2 wt% - Free of dirt									
Additional Notes:									

Operating Procedure
Title: Inspection of Scrap

Appendix A: Examples of Non-Conformances

Low Density



Operating Procedure
Title: Inspection of Scrap



Operating Procedure
Title: Inspection of Scrap

Copper, Lead, Aluminum



Operating Procedure
Title: Inspection of Scrap

Dirt and Concrete



Operating Procedure
Title: Inspection of Scrap

Sealed Containers



Operating Procedure
Title: Inspection of Scrap

Non-Metallics



Operating Procedure
Title: Inspection of Scrap

Rust and Oxidized Steel



Operating Procedure
Title: Inspection of Scrap

